

## Kelvinite 2200

Halogenated Flame Retardant Polypropylene Compound and Sheet Goods

**Description** Highland Kelvinite 2200 is a halogenated flame retardant polypropylene (FRPP), which meets V-0 UL94 at 0.017", and VTM-0 at 0.010". It is suitable for a wide range of electrical and thermal insulation applications.

**Key Benefits**

- Extruded sheet or roll goods act as a fire retardant barrier.
- Easy to process using thermoforming, die cutting, knife cutting, or kiss cutting.
- Extruded material is available in a range of thicknesses from 0.010" to 0.250".
- Manufactured in the USA with a 4 week lead time.
- Corona treatment available.

**Forms**

- Pelletized compound - 1,000 lb. container, 3' x 3' x 5'
- Extruded sheet or rollstock - custom sizes available

**Appearance** Black

Property	Nominal	Method
Flammability	VTM-0, V-0	UL 94

Property	Nominal	Method
Tensile Yield	3700 psi	ASTM D882
Izod Impact	300 J/m	ASTM D-256
Elongation	278 %	ASTM D-882
Flex Modulus	288,000 psi	ASTM D-790
Living Hinge Performance (cycles)	>225,000	MIT Testing Procedure @ 0.010"
Density	1.045	ASTM D-792

Please contact your Highland Sales Representative to request regulatory information and safety data sheet.

**Disclaimer:**

The information contained in this document is for informational purposes only and should not be used as a substitute for testing to ensure that this product is suitable for its intended use. It is the sole responsibility of the user to determine the suitability of this product for the uses and applications intended by the user or others, to ensure compliance with all federal, state, and local laws, rules, and regulations, and to obtain all necessary certifications, permits, and authorizations. All products supplied by Highland Plastics, Inc. or any of its affiliates or subsidiaries are subject to Highland Plastics, Inc.'s terms and conditions of sale. Highland Plastics does not make, and expressly disclaims, any warranty, express or implied, concerning the product, including the merchantability or fitness of the product for any particular purpose, or concerning the accuracy of any information provided herein. Nothing contained herein constitutes an offer for the sale of any product.

## Kelvinite 2200

Halogenated Flame Retardant Polypropylene Compound and Sheet Goods

Electrical Properties	Property	Nominal	Method
	Volume Resistivity	1 x 10 <sup>16</sup> ohm-cm	ASTM D257
	Breakdown Voltage @ 0.030"	39.9 kV	ASTM D150
	Dissipation Factor	0.0022	ASTM D150
	High Voltage Arc Tracking	0 PLC in/min	UL746a
	Hot Wire Ignition	0 PLC - Seconds	UL746a
	Comparative Tracking Index	0 PLC / 600V	ASTM D3638

### Notes

Kelvinite flame-retardant polypropylenes are ideal for automotive and electrical applications and are backed by a robust domestic supply chain when available. Compounded and extruded in Michigan, USA.

We offer halogenated and non-halogenated Kelvinite formulations to meet automotive and non-automotive flammability standards at low gauges.

#### Disclaimer:

The information contained in this document is for informational purposes only and should not be used as a substitute for testing to ensure that this product is suitable for its intended use. It is the sole responsibility of the user to determine the suitability of this product for the uses and applications intended by the user or others, to ensure compliance with all federal, state, and local laws, rules, and regulations, and to obtain all necessary certifications, permits, and authorizations. All products supplied by Highland Plastics, Inc. or any of its affiliates or subsidiaries are subject to Highland Plastics, Inc.'s terms and conditions of sale. Highland Plastics does not make, and expressly disclaims, any warranty, express or implied, concerning the product, including the merchantability or fitness of the product for any particular purpose, or concerning the accuracy of any information provided herein. Nothing contained herein constitutes an offer for the sale of any product.